

# Product Information

Property	Test Method	Unit	Result
Specific Gravity	ASTM D792	-	1.27
Mold Shrinkage	ASTM D955	%	0.2 – 0.5
Rockwell Hardness	ASTM D785	R-scale	105
Tensile Strength @ Yield	ISO 527	MPa	49
Tensile Strength @ Break	ISO 527	Mpa	23
Elongation @ Yield	ISO 527	%	4.1
Elongation @ Break	ISO 527	%	40
Flexural Strength	ISO 178	Mpa	67
Flexural Modulus	ISO 178	Mpa	1,890
Izod Impact Strength Notched @ 23°C	ISO 180	KJ/m2	7.0
Heat Distortion Temperature @ 0.455MPa / @ 1.820 MPa	ISO 75	°C	72 / 62
Haze	ASTM D1003	%	< 1.0
Transmittance	ASTM D1003	%	90